

	AP-5 PG 64-22	1621		2019-12-30 10:34
	620D503	RT1916213785		2019-12-24 04:00

, @15 kg/m ³	KSM 2002	1000	1050	
(15) cm	KSM 2254	100	140+	
,COC	KSM 2010	260	336	
FOAM ON HEAT,180	KSM 2201	NONE	NONE	
Loss on Heating wt%	KSM 2258	0.6	0.1	
가 ((%)) %	KSM 2252	55	70	
%	KSM 2252	110	96	
(25)	KSM 2252	60 ~ 80	69	
가 mass%	KSM 2202-2	99.0	99.9	
	KSM 2250	44.0 ~ 52.0	47.5	
@120 mm ² /s	ASTM D4402	To be reported	984.1	
@150 mm ² /s	ASTM D4402	To be reported	218.6	
@180 mm ² /s	ASTM D4402	To be reported	72.1	
PG- (7)	KSF 2389	64	64	
PG-	KSF 2389	-22	-22	

신용중

